

Product information

REV2015203

Stuffing-Box-Packing Type 2005 FDA

Material composition

TEADIT packing style 2005 FDA is braided from a new type of proprietary yarn made from expanded PTFE with highly refined mineral filler particles.

Please note: the colour of the actual product might vary from the image on this data-sheet.

Properties

Style 2005 FDA is a very supple packing with consistently high density and flexibility. Fast and simple to install, with minimum maintenance requirements. Because of the malleability of the unique yarn used for this packing, emissions (leakage) can be adjusted very finely and reduced to extremely low levels. Highest chemical resistance, very low coefficient of friction. FDA conformity.

Application areas

Although primarily designed as a valve packing, style 2005 FDA can also be used for slow moving rotating equipment like centrifugal pumps and reciprocating pumps, sliders, mixers, etc

Application media

The unsurpassed chemical resistance of PTFE makes this packing ideal for nearly all - even the most aggressive - media. Also suitable for pharmaceutical and food applications, potable water, solvents, oils, gases, effluents, etc.

Not suitable for

Molten alkali metals and fluorine compounds at high temperatures and pressures.

Benefits

Resistant to nearly all fluids and gases including the most corrosive acids and alkalis. Universal valve packing with extremely long packing life and little maintenance requirements. The special type of filled ePTFE yarn enhances malleability and heat trasfer properties of this packing. Conforms to FDA regulations for use with foodstuffs, potable water and pharmaceutical products.





Temperature:

- temp + temp (°C) 200 280

Pressure:

rotating: reciprocating: static: (bar) 20 150 250

pH: 0-14 density: 1,9 v: (m/s) 5

Tests & Approvals

FDA EU Regulation 1935/2004

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences TEADIT® has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. TEADIT® does not undertake any liability of any kind whatsoever. Please note: the colour of the actual product might vary from the above image on this data-sheet.